

Carburo Long Rod Rectified h6, se utiliza principalmente para procesar fresas de metal duro para el corte de metales

※ Diámetros de varillas largas de carburo de tungsteno de 3 mm a 25 mm, longitud común de 300 mm, 310 mm y 330 mm.



#### Grado Recomendación:

材质名称 (Grade)	WC (%)	CO (%)	晶粒度 Grain size ( $\mu\text{m}$ )	比重 Density ( $\text{g}/\text{cm}^3$ ) $\pm 0.1$	硬度 Hardness (HRA) $\pm 0.5$	断裂韧性 KIC ( $\text{MNm}^{-3/2}$ )	抗折力 TRS ( $\text{kgf}/\text{mm}^2$ )
H09U	91	9	0.3	14.5	93.7	9.2	>350
H12U-T	88	12	0.3	14.2	93.0	9.6	>350
H06U-T	94	6	0.4	14.9	94.5	8.4	>380
H06U	94	6	0.4	14.9	94.0	8.7	>380
H08U	92	8	0.4	14.7	93.6	8.8	>380
H08U-K	92	8	0.4	14.7	93.2	9.0	>380
H12U	88	12	0.4	14.3	92.5	9.4	>350
H10S	90	10	0.6	14.4	92.1	9.9	>350
H10F	90	10	0.8	14.4	91.8	10.9	>350