□□ □□ □□ □□□ □□ □□ □□□ □□□□ □□ □□, □□, □□ □□

## 冷镦模
Cold heading die



尺寸公差
Size of tolerance

| 外径 Outside Diameter | 牌号 Grade | | | | | | |
|---|---|---|---|---|---|---|---|
| | HG6 | HG7 | HD7 | HD8 | HD9 | HD11 | HD12 |
| | 外径极限偏差 Deviation | | | | | | |
| Ø10~Ø30 | +0.3~+0.6 | | | +0.3~+0.6 | | | |
| Ø30~Ø50 | +0.4~+0.7 | | | +0.4~+0.8 | | | |
| Ø50~Ø70 | +0.4~+0.8 | | | +0.4~+1.0 | | | |

| 内径 Inner Diameter | 牌号 Grade | | | | | | |
|---|---|---|---|---|---|---|---|
| | HG6 | HG7 | HD7 | HD8 | HD9 | HD11 | HD12 |
| | 内径极限偏差 Deviation | | | | | | |
| Ø1~Ø10 | -0.2~-0.4 | | | -0.2~-0.4 | | | |
| Ø10~Ø20 | -0.3~-0.8 | | | -0.3~-0.8 | | | |
| Ø20~Ø30 | -0.5~-1.0 | | | -0.8~-1.2 | | | |
| Ø30~Ø40 | -0.8~-1.5 | | | -1.2~-1.5 | | | |
| Ø40 | -1.0 | | | -1.2 | | | |

| 高度 Height | 牌号 Grade | | | | | | |
|---|---|---|---|---|---|---|---|
| | HG6 | HG7 | HD7 | HD8 | HD9 | HD11 | HD12 |
| | 高度极限偏差 Deviation | | | | | | |
| 10~35 | +0.6~+1.0 | | | +0.6~+1.0 | | | |
| 35~45 | +0.8~+1.2 | | | +0.8~+1.5 | | | |
| 45~55 | +1.0~+1.5 | | | +1.0~+1.5 | | | |
| 55~65 | +1.2~+1.8 | | | +1.2~+1.8 | | | |

□□ □□ :

| 牌号 | 钴含量 | WC 晶粒度 | 硬度 | 密度 | 抗弯强度 | 弹性模量 | 冲击韧性 | 适用范围 |
|---|---|---|---|---|---|---|---|---|
| Grade | Co % | Grain Size of WC/um | Hardness HRA ±0.5 | Density g/m³ ±0.1 | Flexural Strength Mpa | Elastic Modulus Gpa | Impact Toughness J/cm2 | Applications |
| HG6 | 15 | 2 | 86.5 | 13.95 | 3000 | 440 | 6.4 | 耐磨、耐冲击要求比较高的工程齿、冷锻模具。<br>Suitable for Engineering Teeth,Cold Forging Die, with High Wear and Impact Resistance. |
| HG7 | 18 | 2 | 85 | 13.75 | 2800 | 410 | 7.4 | |
| HD9 | 24 | 2 | 82 | 13.10 | 2800 | 340 | 10 | |
| HD11 | 21 | 2 | 84.5 | 13.45 | 2800 | 340 | 8.2 | 具有高韧性、耐冲击性、耐热冲击性等优点，适用于在对耐冲击性要求比较高的冷间锻造领域。<br>Suitabale for Strict Requirement Cold Forging Area, with High Toughness, Impact Resistance and Heat Resistance. |
| HD12 | 24 | 2 | 82.5 | 13.15 | 2800 | 340 | 10.4 | |