

Carbide Long Rod Rectified h6, is mainly used for processing solid carbide end mills for metal cutting

※ Tungsten carbide long rods diameter from 3mm-25mm, common length 300mm, 310mm, and 330mm.



Grade Recommendation:

材质名称 (Grade)	WC (%)	CO (%)	晶粒度 Grain size (um)	比重 Density (g/cm³) ±0.1	硬度 Hardness (HRA) ±0.5	断裂韧性 KIC (MNm-3/2)	抗折力 TRS (kgf/mm²)
H09U	91	9	0.3	14.5	93.7	9.2	>350
H12U-T	88	12	0.3	14.2	93.0	9.6	>350
H06U-T	94	6	0.4	14.9	94.5	8.4	>380
H06U	94	6	0.4	14.9	94.0	8.7	>380
H08U	92	8	0.4	14.7	93.6	8.8	>380
H08U-K	92	8	0.4	14.7	93.2	9.0	>380
H12U	88	12	0.4	14.3	92.5	9.4	>350
H10S	90	10	0.6	14.4	92.1	9.9	>350
H10F	90	10	0.8	14.4	91.8	10.9	>350