

Ganzhou Grand Mar Cemented Carbide Co, .LTD é a subsidiária integral do Granzhou Grand Sea Group que é joint venture sino-estrangeiro investido pela Kyocera Corporation.


Agora carboneto inserir projeto é o projeto chave de desenvolvimento de Grande Mar Cemented Carbide. Carboneto, Grand Mar tem 5 prensas elétricas importadas do Japão, produzindo carboneto inserir 2 milhões por mês.

Nossa Vantagem

1. 100% matéria-prima de carboneto de tungstênio.
2. P & D e capacidade de produção de acompanhar as tendências do mercado.
3. Capacidade de suporte técnico para resolver soluções de processamento para clientes em todos os aspectos.
4. estoque adequado para garantir a entrega rápida.
5. Somos o fornecedor que pode atacado e personalizado as inserções de carboneto para você.

A recomendação GARDE:

Grau	banheiro %	Co. %	Tamanho de grão (hum)	Densidade (g / cm ³) ± 0,1	Dureza (HRA) ± 0,5	Trs. (kgf / mm ²)
H10F.	90.	10.	0.8.	14.40.	91.8.	> 350.
H11F.	87.	12.	0.3.	14,50.	91.4.	> 350.
H12A.	88.	22.	1.2.	14.20.	90.5.	> 350.



1 2 3 4 5 6 7 8 9 10
C N M G 12 04 08 (E) (N)-MP

1. Insert Shape

1. Insert Shape		
Symbol	Insert Shape	
H	Hexagonal	
O	Octagonal	
P	Pentagonal	
S	Square	
T	Triangular	
C	Rhombic 80°	
D	Rhombic 55°	
E	Rhombic 75°	
F	Rhombic 50°	
M	Rhombic 86°	
V	Rhombic 35°	
W	Trigon	
L	Rectangular	
A	Parallelogram 85°	
B	Parallelogram 82°	
K	Parallelogram 55°	
R	Round	
X	Special Design	

2. Relief Angle

2. Relief Angle		
Symbol	Normal Clearance	
A	3°	
B	5°	
C	7°	
D	15°	
E	20°	
F	25°	
G	30°	
N	0°	
P	11°	
O	Other Relief Angle	
Major Relief Angle		

3. Tolerance Class

3. Tolerance Class										
3. Tolerance Class				Detail of M Class Insert Tolerance						
Symbol	Tolerance of Nose Height M (mm)	Tolerance of Inscribed Circle IC (mm)	Tolerance of Thickness S (mm)	●Tolerance of Nose Height M (mm)						
				D.I.C.	Triangular	Square	Rhombic 80°	Rhombic 55°	Rhombic 35°	Round
A	±0.005	±0.025	±0.025	6.35	±0.08	±0.08	±0.08	±0.11	±0.16	—
F	±0.005	±0.013	±0.025	9.525	±0.08	±0.08	±0.08	±0.11	±0.16	—
C	±0.013	±0.025	±0.025	12.70	±0.13	±0.13	±0.13	±0.15	—	—
H	±0.013	±0.013	±0.025	15.875	±0.15	±0.15	±0.15	±0.18	—	—
E	±0.025	±0.025	±0.025	19.05	±0.15	±0.15	±0.15	±0.18	—	—
G	±0.025	±0.025	±0.13	25.40	—	±0.18	—	—	—	—
J	±0.005	±0.05—±0.15	±0.025	31.75	—	±0.20	—	—	—	—
K*	±0.013	±0.05—±0.15	±0.025	●Tolerance of Inscribed Circle IC (mm)						
L*	±0.025	±0.05—±0.15	±0.025	D.I.C.	Triangular	Square	Rhombic 80°	Rhombic 55°	Rhombic 35°	Round
M*	±0.08—±0.18	±0.05—±0.15	±0.13	6.35	±0.05	±0.05	±0.05	±0.05	±0.05	—
N*	±0.08—±0.18	±0.05—±0.15	±0.025	9.525	±0.05	±0.05	±0.05	±0.05	±0.05	±0.05
U*	±0.13—±0.38	±0.08—±0.25	±0.13	12.70	±0.08	±0.08	±0.08	±0.08	—	±0.08
The surface of insert with * mark is sintered.				15.875	±0.10	±0.10	±0.10	±0.10	—	±0.10
				19.05	±0.10	±0.10	±0.10	±0.10	—	±0.10
				25.40	—	±0.13	—	—	—	±0.13
				31.75	—	±0.15	—	—	—	±0.15

4. Chipbreaker and Clamping System

4. Chipbreaker and Clamping System									
Metric									
Symbol	Hole	Hole Configuration	Chip Breaker	Figure	Symbol	Hole	Hole Configuration	Chip Breaker	Figure
W	With Hole	Cylindrical Hole	No		A	With Hole	Cylindrical Hole	No	
T	With Hole	One Countersink (40–60°)	One Sided		M	With Hole	Cylindrical Hole	Single Sided	
Q	With Hole	Cylindrical Hole	No		G	With Hole	Cylindrical Hole	Double Sided	
U	With Hole	Double Countersink (40–60°)	Double Sided		N	Without Hole	—	No	
B	With Hole	Cylindrical Hole	No		R	Without Hole	—	Single Sided	
H	With Hole	One Countersink (70–90°)	One Sided		F	Without Hole	—	Double Sided	
C	With Hole	Cylindrical Hole	No		X	—	—	—	Special Design
J	With Hole	Double Countersink (70–90°)	Double Sided						

5. Insert Size

5. Insert Size							
Symbol							Diameter of Inscribed Circle (mm)
R	W	V	D	C	S	T	
	02		04	03	03	06	3.97
	L3	08	05	04	04	08	4.76
	03	09	06	05	05	09	5.56
06							6.00
	04	11	07	06	06	11	6.35
	05	13	09	08	07	13	7.94
08							8.00
09	06	16	11	09	09	16	9.525
10							10.00
12							12.00
12	08	22	15	12	12	22	12.70
15	10		19	16	15	27	15.875
16							16.00
19	13		23	19	19	33	19.05
20							20.00
			27	22	22	38	22.225
25							25.00
25			31	25	25	44	25.40
31			38	32	31	54	31.75
32							32.00

6. Insert Thickness

6. Insert Thickness	
 <p>*Thickness is from the bottom of the insert to the top of the cutting edge.</p>	
Symbol	Thickness (mm)
S1	1.39
01	1.59
T0	1.79
02	2.38
T2	2.78
03	3.18
T3	3.97
04	4.76
06	6.35
07	7.94
09	9.52

7. Insert Corner Configuration

7. Insert Corner Configuration	
Symbol	Corner Radius (mm)
00	Sharp Nose
V3	0.03
V5	0.05
01	0.1
02	0.2
04	0.4
08	0.8
12	1.2
16	1.6
20	2.0
24	2.4
28	2.8
32	3.2
00 : Inch M0 : Metric	Round Insert

8. Cutting Edge Condition

8. Cutting Edge Condition		
Figure	Cutting Edge	Symbol
	Sharp Cutting Edges	F
	Round Cutting Edges	E
	Chamfered Cutting Edges	T
	Chamfered and Rounded Cutting Edges	S
Mitsubishi Materials omit the honing symbol.		

9. Cutting Direction

9. Cutting Direction		
Figure	Hand	Symbol
	Right	R
	Left	L
	Neutral	N

10. Chip Breaker

10. Chip Breaker		
LP	MP	RP
LM	MM	RM
LK	MK	RK
LS	MS	RS
FP	LP	MP
MA	SW	MW
HZ	HX	HV