

| 材质名称 (Grade) | WC (%) | CO (%) | 晶粒度 Grain size (μm) | 比重 Density (g/cm^3) ± 0.1 | 硬度 Hardness (HRA) ± 0.5 | 抗折力 TRS (kgf/mm^2) |
|-----------------|-----------|-----------|----------------------------------------|-------------------------------------------------------|-----------------------------------|--------------------------------------------|
| HG2 | 94 | 6 | 1.2 | 14.95 | 91.3 | >280 |
| HG3 | 92 | 8 | 1.2 | 14.75 | 90.5 | >280 |
| HG4 | 90 | 10 | 1.2 | 14.50 | 90.0 | >280 |
| HG5 | 88 | 12 | 1.2 | 14.30 | 89.0 | >280 |
| HG6 | 85.5 | 14.5 | 2.0 | 14.00 | 86.5 | >300 |
| HG7 | 83.4 | 16.6 | 1.6 | 13.75 | 85.5 | >280 |
| H12S | 88 | 12 | 0.6 | 14.25 | 91.5 | >350 |
| HGF20 | 88.5 | 11.5 | 0.8 | 14.25 | 91.0 | >320 |
| HGF25 | 87 | 13 | 1.0 | 14.10 | 90.0 | >320 |
| HGF30 | 85 | 15 | 1.0 | 13.90 | 89.0 | >320 |
| HD9 | 78 | 22 | 2.0 | 13.05 | 82.5 | >280 |
| HD11 | 79 | 21 | 1.6 | 13.45 | 84.5 | >280 |
| HD12 | 76 | 24 | 2.0 | 13.15 | 83.0 | >280 |

□□□□□□□□□□

