

品名	硬度 %	重量 %	厚度 (mm)	密度 (g / cm ³) ± 0.1	冲击 (HRA) ± 0.5	trs (kgf / mm ²)
he10	94	6	1.6	14.95	90.4	> 300
he15	94	6	2.0	14.95	89.6	> 280
HE16	94	6	3.2	14.95	88.2	> 270
he20	92	8	3.2	14.75	87.8	> 270
he30	91	9	3.2	14.65	87.5	> 260
HE35	89	11	3.2	14.40	86.8	> 250
he36	88	12	2.0	14.30	87.0	> 280
he40	87	13	3.2	14.20	85.5	> 240
he50	85	15	3.2	14.05	85.0	> 230
HAC3	94	6	4.0	14.95	88.3	> 240
tc02	91.5	8.5	6.0	14.65	86.4	> 240

